
# Investigation of Adsorption and Dissociation of the O<sub>2</sub> Molecule on W(111) Surface: A Density Functional Theory Study

**Reporter: Meng-Hsiung Weng** 


**Advisor: Shin-Pon Ju** 

Department of Mechanical and Electro-Mechanical Engineering; Center for Nanoscience and Nanotechnology, National Sun Yat-Sen University, Kaohsiung 804, Taiwan



### Catalysis

#### Three-Way Converter (TWC): Pt, Rh, Pd






Pt, Pd :  $CO \longrightarrow CO_2$   $HC \longrightarrow CO_2 + H2O$ Rh :  $NOx \longrightarrow N_2 + O_2$ 

### Catalysis of O<sub>2</sub> molecule on W metal surface.

Catalyst: Tungsten (W)





#### Pictures source:

### Potential Application of Tungsten Carbides as Electrocatalysts. 2. Coadsorption of CO and H<sub>2</sub>O on Carbide-Modified W(111)

#### Henry H. Hwu, Brian D. Polizzotti, and Jingguang G. Chen\*

Center for Catalytic Science and Technology, Department of Materials Science and Engineering, University of Delaware, Newark, Delaware 19716

Received: April 27, 2001; In Final Form: July 11, 2001

The decomposition of water and CO over clean and carbide-modified W(111) is studied by using temperature-programmed desorption (TPD), high-resolution electron energy loss spectroscopy (HREELS), and auger electron spectroscopy (AES). On both clean and modified W(111) surfaces, the activity toward the decomposition of water is found to be significantly higher than Pt group metals. For the CO experiments, both molecular and dissociative adsorption are observed on W(111) and C/W(111). Approximately 52% and 10% of the adsorbed CO dissociates to produce atomic oxygen and carbon on W(111) and C/W(111), respectively. In contrast, CO molecules undergo reversible desorption on oxygen-modified C/W(111) at temperatures as low as 242 K. Finally, coadsorption experiments of water and CO on C/W(111) show that the presence of surface hydroxyls hinders the adsorption of CO, and that only trace amount of gas-phase CO<sub>2</sub> is detected.




#### Adsorption and Dissociation of the HCl and Cl<sub>2</sub> Molecules on W(111) Surface: A Computational Study


Hui-Lung Chen,<sup>†</sup> Shin-Pon Ju,\*,<sup>‡</sup> Hsin-Tsung Chen,<sup>§</sup> Djamaladdin G. Musaev,\*,<sup>†</sup> and M. C. Lin\*,<sup>†</sup>,<sup>§</sup>

Cherry L. Emerson Center for Scientific Computation and Department of Chemistry, Emory University, Atlanta, Georgia 30322, Department of Mechanical and Electro-Mechanical Engineering, Center for Nanoscience and Nanotechnology, National Sun-Yat-Sen University Kaohsiung, Taiwan 804, and Center for Interdisciplinary Molecular Science, Institute of Molecular Science, National Chiao Tung University, Hsinchu, Taiwan 300

Received: January 12, 2008; Revised Manuscript Received: April 21, 2008




## Simulation model for W(111)



Side view

Top view

### Adsorbed sites



On top (T): On the top of the first layer W1 atom.

Bridge (B): On between the first layer W1 and second layer W2 atoms.

3-fold-Deep (D): On the top of the third layer W3 atom.

3-fold-Shallow (S): On the top of the second layer W2 atom.

# DFT calculation:

Package: VASP

Functional: rPBE

Cutoff energy: 400 eV

Spin polarization

Energy convergence: 1\*10<sup>-4</sup>eV

#### **Bulk W:**


Bulk W	Lattice constants(Å)	W-W distance(Å)
This work	3.170	2.745-2.754
Experiment value	3.165 <sup>a</sup>	2.741 <sup>a</sup>

a. Villars, P.; Calvert, L. D. *Pearson's Handbook of Crystallographic Data for Intermetallic Phase*, 2nd ed.; ASM International: Materials Park, OH, 1991.

### O<sub>2</sub> molecule:

$\mathbf{O}_2$	Bond length(Å)
This work	1.23
Experiment value	1.21

### Optimized geometries of adsorbed 0 atom on W(111)




Top (T)


1.817



3-fold-shallow (S)



Bridge (B)



3-fold-deep (D)

## ŊΑ

## Optimized Structural Parameters and Adsorption Energies<sup>a</sup> of O atoms adsorbed on W (111) surface.

	Bond length O-W (Å)	Adsorption energy	
top (T)	1.741	- 155.54	
bridge (B)	1.985,1.947	- 154.17	
3-fold-deep(S)	2.283	- 146.80	
3-fold-shallow( <b>D</b> )	1.819	- 137.21	

<sup>&</sup>lt;sup>a</sup> The unit of energy is kcal/mol.

## Vibrational Frequencys<sup>a</sup> of O adsorbed on the W(111) surface:

Site	V(W-O)
On-top (T)	884
Bridge ( <b>B</b> )	586
3-fold-deep( <b>D</b> )	524
3-fold-deep( <b>D</b> )	643

Experiment value: 400 – 800cm<sup>-1</sup>


<sup>a</sup>The unit of Vibrational Frequencys is wavenumber(cm-1)



## 02 on W(111) surface

#### **End-On:**

### Optimized geometries of adsorbed 02 molecule on W(111)






## Optimized Structural Parameters and Adsorption Energies<sup>a</sup> of O2 atoms adsorbed on W (111) surface.

	Bond length	Bond length	Adsorption
	$O_a$ - $W(A)$	O-O (Å)	energy
top (T)	1.827	1.315	-44.30
bridge (B)	2.012	1.382	-23.4
3-fold-shallow(S)	) 1.892	1.322	-24.2
3-fold-deep(D)	2.805	1.328	14.30

<sup>&</sup>lt;sup>a</sup> The unit of energy is kcal/mol.



### Side- On



On-Top(T)

Side-on	Length(W-O) (Å)	Length (O-O)	$\mathbf{E_{ad}}$ (Kcal/mol)
		(Å)	
On-Top (T)	1,955 ; 1.967	1.488	-65.55
Bridge (B)	N/A	N/A	N/A
Deep (D)	N/A	N/A	N/A
Shallow (S)	N/A	N/A	N/A

### Dissociation of $O_2$ on W(111) surface.


#### Reaction:

$$O2 + W(111) \rightarrow O/W(111)/O$$

#### Nudged elastic band (NEB) Method:

- **1. 16 Images**
- 2. Energy convergence: 1\*10<sup>-4</sup> eV
- 3. Force convergence: 0.04 eV/A

### Potential energy profiles for O2-W(111)



Reaction coordination




### **DFT –MD simulation**


Temperature: 10 K

canonical ensemble (NVT)

Time step: 2fs




Side view




Top view


## M



**Fig.** Snapshots of the  $O_2$  dissociation on the W(111) surface at (a) 0, (b) 1400, (c) 1600, and (d) 2400 fs. The blue and red spheres represent W, and O, respectively. The bond lengths are given in Å.





## M



**Figure 4.** Snapshots of the  $O_2$  adsorption on the W(111) surface at (a) 0, (b) 400, (c) 540, and (d) 720 fs. The blue and red spheres represent W, and O, respectively. The bond lengths are given in Å.

#### Second O2 deposition: Without dissociation





## M

#### Second O2 deposition





Fig. Snapshots of the second O2 molecules on the W(111) surface after the dissociation of first O2 molecules at


- (a) 0, (b) 1000, (c) 1400, and (d) 1700 fs. The blue and Red spheres represent W, and O, respectively.
- (b) The bond lengths are given in Å. (red dash circles respect the oxygen atoms by repeat of periodic boundary)



#### Third O2 deposition



#### Third O2 deposition





### Conclusions:

- 1. The preferable sites of O atom and  $O_2$  molecules on W(111) surface is top site. the calculated adsorption energy are -158.8, -46.3 kcal/mol for O and  $O_2$ , respectively.
- 2. The MEP profile from NEB calculations indicate that there is small barrier for the dissociation of O2 molecule.
- 3. O<sub>2</sub> molecule will always be dissociated by inclined deposition at temperature of 10K, but case of O<sub>2</sub> molecule without dissociation can still be found to adsorb at top site without rotation and angular momentum.
- 4. O2 molecule prefers initially to adsorb at top site and the neighbor environment of O<sub>2</sub> molecule after adsorption determine whether dissociation occurs.



# Thank You!!